



NIPPELUX TROPICAL ANTI-FOULING

TYPE	A classical anti-fouling paint with a high percentage of cuprous oxide.
USES	Protection against marine growth on ship bottoms.
SPECIAL FEATURES	Offers efficient and lasting protection against marine growth on ship bottoms.
TEXTURE	Semi-gloss.
SURFACE DRY	1 hour at 20°C or 40 minutes at 30°C.
HARD DRY	10 hours at 20°C or 6 hours at 30°C.
OVERCOATING INTERVAL	16 hours at 20°C or 12 hours at 30°C.
IMMERSION IN WATER	16 hours at 20°C or 12 hours at 30°C.
NON-VOLATILE CONTENT	60.0% by volume.
FILM THICKNESS - WET	85 microns.
FILM THICKNESS - DRY	50 microns.
THEORETICAL COVERAGE	12.0 sq. metres per litre.
PRACTICAL COVERAGE	9.6 sq. metres per litre (loss factor 20%).
SPECIFIC GRAVITY	1.54 kg per litre.
THINNER	1901 Nippelux Thinner.
FLASH POINT	32°C.
COLOUR	Red Brown.
STANDARD PACKING	5 litres and 20 litres.
SURFACE PREPARATION	The surface must be clean and dry, free from grease and oil.
PAINT PREPARATION	Ready for use after thorough stirring.
APPLICATION – AIRLESS SPRAY	Delivery Pressure: 140-170 kg/cm ² . Tip Size: 0.017" at 60° angle. 0.019" at 60° or 70° angle. Dilution: 0-5%. Film Thickness – Wet: 85 microns per coat Dry: 50 microns per coat.
APPLICATION – BRUSH OR ROLLER	Dilution: 0-5%.
PRECAUTIONS	It contains volatile and inflammable solvents. Ensure adequate ventilation during use, avoiding naked flame, welding operations and other fires. Avoid contact with skin.
NOTE	Values given are average for reference. Actual values may vary, depending on conditions.