



COLD GALVANIZING Spray

DESCRIPTION	Zinc- rich coating used to touch- up damaged or weathered galvanized surfaces such as gutters and fences. Dry film contains 93% zinc.
APPEARANCE	Flat gray
RECOMMENDED TOPCOATS	No top coat necessary but if one is desired, use a water based product. If an oil based (alkyd) product is the desired finish, use a water based primer as an intermediate coat.
FILL WEIGHT	16 oz. (454 g)
SURFACE PREPARATION	Remove all dirt, grease, oil, salt and chemical contaminants by washing the surface with commercial detergent or other suitable cleaner. Rinse thoroughly with fresh water and allow to fully dry.
APPLICATION	Use in a well ventilated area. Spraying can produce a fog that will travel. Protect surrounding area, clothing and skin from overspray. Shake can vigorously for one minute after the mixing ball begins to rattle. Shake often during use. Hold can upright 12-16 inches for the surface and spray in a steady back-and-forth motion, slightly overlapping each stroke. Keep the can the same distance for the surface and in motion while spraying.
CLEAN-UP	When finished spraying, clear spray valve by turning can upside down and pushing spray button for 5 seconds. If valve clogs, twist and pull off spray tip and rinse it in a solvent such as mineral spirits. Do not stick a pin or other object into the stem. Throw away empty can in trash pickup. Do not burn or place in home trash compactor.

PHYSICAL PROPERTIES (Calculated values are shown and may vary slightly from the actual manufactured material)

RESIN TYPE	Epoxy Ester
SOLVENTS	Toluene, Mineral Spirits
PRACTICAL COVERAGE	Approximately 10-12 sq. ft./can (0.9 – 1.1 m ²)
DRY TIMES @70°F (21°C) and 50% RH	
	Touch 10 - 20 minutes
	Handle 1-2 hours
	Recoat Within 1 hour or after 24 hours
VOLATILE ORGANIC COMPOUND	<60%
SHELF LIFE	5 years
FLASH POINT	-156° F (-144° C)
LEAD FREE	